

ASA Pro-DM

ASA Pro-DM is our highly modified “industrial-grade” ASA filament with many features like UV resistance, zero warp technology and excellent mechanical properties. ASA Pro-DM is the perfect replacement when you require a performance material without the problems that can arise during printing with, for example, ABS. ASA Pro-DM not only has great strength and interlayer adhesion but also features one of the best aesthetics possible with FDM 3D printing. The reliable bed adhesion will ensure a smooth printing experience. ASA Pro-DM is perfect when you are looking for beautiful and strong prints that also last outside.


Material features:

- UV / Weather resistant
- Zero warp technology
- Excellent interlayer adhesion
- Great strength & aesthetics
- Reliable bed adhesion (Glass, tape & other adhesives)



Colors :

ASA Pro-DM is available from stock in 7 industrial colors.



Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Test method	Typical value
Specific gravity	ISO 1183	1,11 g/cc
MFR 220 °C/10 kg	ISO 1133	26,6 gr/10 min
Tensile Strength at Yield	ISO 527	47,5 Mpa
strain at break	ISO 527	15%
Tensile modulus	ISO 527	2020 Mpa
Impact strength - Charpy notched 23°C	ISO 179	18 kJ/m2
Printing temp.	DF	245 ±10°C
Melting temp.	ISO 294	230 ±10°C
Vicat softening temperature	ISO 306	98°C

Additional info:

Recommended temperature for heated bed is ± 80 -90°C.

ASA Pro-DM is printed at high temperatures to make the final product extra strong. ASA Pro-DM can be used on all common desktop FDM or FFF technology 3D printers. Storage: Cool and dry (15 -25°C). This enhances the shelf life significantly.